

**paraffin for votives, molded candles, and
all around candle making**

Paraffin wax 3134



Test Description	ASTM Method	Minimum	Maximum	Typical
Melting Point °F / °C	D 87	130/54	132/56	131/55
Penetration @ 77°F/25°C	D 1321		18	16
Color Saybolt	D 156	+30		+30
Oil Content WT%	D 721		0.5	0.4
Flash, PM °F/°C	D 93	400/204		405/207
Viscosity, SUS, 210°F/98.9°C	D 2161	38	41	39
Viscosity, cSt, 210°F/98.9°C	D 445	3.6	4.5	3.9
Odor	D 1833		2	1

Recommendations

- ☞ Additives are recommended for optimum results.
- ☞ Pouring temperature can range from 170° - 190° F, depending on application.
- ☞ Common additives used - Stearic (2-10%), Mico 180 (1-5%), Vybar 103 (1-2%), C-15 (1-3%).

Packaging

- ☞ 3134 is available in 50 lb. cases - 40 cases per pallet (2,000 lbs.) - Slab on pallet is 2,100 lbs.
- ☞ Available slab on pallet and cases in PA.
- ☞ 3134 is available prilled packaged in 25# cases - only available in PA.
- ☞ Available in cases only from Chicago, IL.

FDA Status

- ☞ 2134 is a food grade paraffin that is manufactured in compliance with FDA regulations covered under Title 21, sections 172.886 and 178.3710.



The Candlewic Company

825 Easton Road, Doylestown, PA 18901 | 8244 Easton Road, Ottsville, PA 18942
Doylestown, PA: 800-368-3352 | Ottsville: 610-847-3069 | www.candlewic.com