

paraffin for jars, containers and sand casting

Paraffin wax Container Fill



Test Description	ASTM Method	Minimum	Maximum	Typical
Melting Point °F / °C	D 87	120/49	125/52	122/50
Penetration @ 77°F/25°C	D 1321		50	35
Color Saybolt	D 156	+25		+25
Oil Content	D 721		2.0	1.5
Flash, PM °F/°C	D 93	380/193		400/204
Viscosity, SUS, 210°F/98.9°C	D 2161	36	40	38
Viscosity, cSt, 210°F/98.9°C	D 445	2.9	4.2	3.6
Odor	D 1833		2	1

Recommendations

- ☞ Additives are recommended for optimum results.
- ☞ Pouring temperature can range from 170° - 190° F, depending on application.
- ☞ Common additives used in this paraffin wax - Mico 845, Vybar 260, Petrolatum & Astorlite C.
- ☞ Always use Ultralight Absorbers to prevent fading.

Packaging

- ☞ Container Fill is available in 50 lb. cases - 40 cases per pallet (2,000 lbs.) - slab on pallet is 2,100 lbs.
- ☞ Available slab on pallet and cases in PA.
- ☞ Available in cases only from Chicago, IL.



The Candlewic Company

825 Easton Road, Doylestown, PA 18901 | 8244 Easton Road, Ottsville, PA 18942
Doylestown, PA: 800-368-3352 | Ottsville: 610-847-3069 | www.candlewic.com